

Technical Data Sheet

STRUKTOL® TS 35-DL

Tackifier and Plasticiser

Composition

Aliphatic-aromatic soft resin (67 %) on silica carrier (33 %)

Properties

Appearance		Light, crumbly powder
Density	[kg/m ³]	1200
Bulk density	[kg/m ³]	600
Ash content	[%]	31
Physiological behaviour		Refer to safety data sheet
Storage stability		At least 24 months under normal storage conditions
Packaging		20 kg bags





Recommendations for Application

STRUKTOL® TS 35-DL is the Dry Liquid form of the viscous resin. As free-flowing powder it offers improved handling over the viscosity product STRUKTOL® TS 35.

STRUKTOL® TS 35-DL contains a resinous plasticiser which significantly increases the low green tack of synthetic rubber compounds, while the storage stability and cure rate of those compounds are not influenced.

The processability of compounds is improved by the addition of STRUKTOL® TS 35-DL. Furthermore, a good dispersion of carbon black and mineral fillers is achieved.

The physical properties vary only within the generally accepted rate for plasticizers. The low temperature flexibility is not influenced by STRUKTOL® TS 35-DL compared to most other synthetic plasticisers.

Having a good resistance to extractability by aliphatic hydrocarbons and mineral oils STRUKTOL® TS 35-DL is recommended for oil-resistant compounds.

Dosage

5 – 25 phr



Disclaimer:

This publication is not a specification and does not contain any instruction manual or operating guidelines. It is provided for information purposes only and without any responsibility. Schill + Seilacher "Struktol" makes no representations about the accuracy, reliability or completeness of the information in this publication. We reserve the right to revise our not specified products and the information at any time without notice. The information in this publication is based on the present state of our knowledge and experience and serves the general description of our products and their possible applications. Our technical advice and recommendations, whether verbal, in writing or by way of trials, do not absolve the recipient, on account of the many outside influences which may affect the product use and application, from their own testing and trials. A legally binding assurance based on the information contained herein regarding particular properties or the suitability for definite customer applications cannot be derived from our information.

In accordance with the provisions of our General Terms and Conditions of Sale and Delivery, which can be accessed under www.struktol.de, Schill+Seilacher "Struktol" excludes liability for slightly negligent breaches of obligations arising from the use of the information contained in this publication, provided that they do not relate to damage from injury to life, limb or health or guarantees or claims under the Product Liability Act are affected. Furthermore, the liability for the breach of obligations, the fulfilment of which is essential for the proper execution of the contract and on the observance of which the customer may regularly rely, remains unaffected. The same applies to breaches of duty by our agents.

This technical datasheet is created automatically and is valid without signature.

