

Technical Data Sheet

STRUKTOL® AKTIVATOR 73 A

Vulcanization Activator for Natural Rubber

Composition

Mixture of zinc salts of aliphatic and aromatic carboxylic acids

Properties

Appearance		Light-grey pastilles
Density	[kg/m ³]	1200
Bulk density	[kg/m ³]	750
Dropping point	[°C]	112
Zinc content	[%]	16.3
Physiological behaviour		Refer to safety data sheet
Storage stability		At least 24 months under normal storage conditions
Packaging		20 kg bags



Recommendations for Application

STRUKTOL® AKTIVATOR 73 A, a formulation of selected zinc salts, is a very effective activator for the sulphur vulcanization of diene rubbers, especially natural rubber.

STRUKTOL® AKTIVATOR 73 A is a low odour version of STRUKTOL® AKTIVATOR 73.

STRUKTOL® AKTIVATOR 73 A can partly or totally replace conventional activators based on fatty acids, e.g. stearic acid, zinc stearate and zinc-2-ethylhexanoate.

The following improvements are achievable by application of STRUKTOL® AKTIVATOR 73 A:

- prolonged reversion time
- higher modulus
- reduced compression set at elevated temperatures.

Further, STRUKTOL® AKTIVATOR 73 A can be used as an effective physical peptiser for the mastication of natural rubber.

Dosage



Disclaimer:

This publication is not a specification and does not contain any instruction manual or operating guidelines. It is provided for information purposes only and without any responsibility. Schill + Seilacher "Struktol" makes no representations about the accuracy, reliability or completeness of the information in this publication. We reserve the right to revise our not specified products and the information at any time without notice. The information in this publication is based on the present state of our knowledge and experience and serves the general description of our products and their possible applications. Our technical advice and recommendations, whether verbal, in writing or by way of trials, do not absolve the recipient, on account of the many outside influences which may affect the product use and application, from their own testing and trials. A legally binding assurance based on the information contained herein regarding particular properties or the suitability for definite customer applications cannot be derived from our information.

In accordance with the provisions of our General Terms and Conditions of Sale and Delivery, which can be accessed under www.struktol.de, Schill+Seilacher "Struktol" excludes liability for slightly negligent breaches of obligations arising from the use of the information contained in this publication, provided that they do not relate to damage from injury to life, limb or health or guarantees or claims under the Product Liability Act are affected. Furthermore, the liability for the breach of obligations, the fulfilment of which is essential for the proper execution of the contract and on the observance of which the customer may regularly rely, remains unaffected. The same applies to breaches of duty by our agents.

This technical datasheet is created automatically and is valid without signature.

