

Technical Data Sheet

STRUKTOL® SU 109

Preparation of Insoluble Sulphur

Composition

Total sulphur	75 %
Organic dispersing agent	24 %
Inorganic dispersing agent	1 %

Properties

Appearance		Non-dusting powder
Density	[kg/m ³]	1530
Bulk density	[kg/m ³]	450
Content of insoluble sulphur	[%]	73
Physiological behaviour		Refer to safety data sheet
Storage stability		At least 18 months under normal storage conditions in closed bags in cool rooms (keep away from ammonia and amine containing compounds)
Packaging		20 kg bags
Factor for dosage		1.33



Recommendations for Application

Two basic types of sulphur are used for rubber compounding, i.e. ordinary ground sulphur called „soluble sulphur“ because of its solubility in carbon disulphide (CS₂) and the so-called insoluble sulphur insoluble in CS₂.

This characteristic of the sulphur types is paralleled by their solubility in rubbers: insoluble sulphur is completely insoluble in rubber whilst ground sulphur is in part soluble. This solubility depends upon temperature and excessive sulphur crystallizes from a compound mixed at higher temperatures.

A greyish sulphur bloom appears on the uncured compound surface followed by small sulphur crystals which can no more be dispersed in the rubber compound.

Consequences of sulphur blooming are:

- increased scorch risk in areas where sulphur has concentrated
- decreased building tack
- local overcure
- variations in physical properties

When using insoluble sulphur blooming from the uncured compound can be avoided. Whilst ordinary ground sulphur is easily incorporated/dispersed in most rubber compounds insoluble sulphur can give rise to problems. Owing to static electricity agglomerates are formed which are only partially dispersed.

The specialty dispersing agents contained in STRUKTOL® SU 109 effect a fast incorporation and optimum sulphur dispersion. Static electricity build-up is minimized. The dispersing agents used are non-discolouring and have no influence on the cure rate. The best dispersion performance can be achieved in a mixing temperature range between 60 – 80 °C.

STRUKTOL® SU 109 containing 75 % of sulphur is used where a low content of dispersing agent is desirable.

When using insoluble sulphur it is important to recognize that this form reverts to soluble sulphur at elevated temperatures, i.e. it should be admixed at temperatures below the critical reversion point (80 °C). This also applies to any further processing of the finalized compound.

It is also important to note that the reversion of insoluble sulphur is not only promoted through temperature, but also through inorganic bases (amines). Special attention must be paid to the accelerator system in compounding and care should be taken that activators are not too alkaline.



Disclaimer:

This publication is not a specification and does not contain any instruction manual or operating guidelines. It is provided for information purposes only and without any responsibility. Schill + Seilacher "Struktol" makes no representations about the accuracy, reliability or completeness of the information in this publication. We reserve the right to revise our not specified products and the information at any time without notice. The information in this publication is based on the present state of our knowledge and experience and serves the general description of our products and their possible applications. Our technical advice and recommendations, whether verbal, in writing or by way of trials, do not absolve the recipient, on account of the many outside influences which may affect the product use and application, from their own testing and trials. A legally binding assurance based on the information contained herein regarding particular properties or the suitability for definite customer applications cannot be derived from our information.

In accordance with the provisions of our General Terms and Conditions of Sale and Delivery, which can be accessed under www.struktol.de, Schill+Seilacher "Struktol" excludes liability for slightly negligent breaches of obligations arising from the use of the information contained in this publication, provided that they do not relate to damage from injury to life, limb or health or guarantees or claims under the Product Liability Act are affected. Furthermore, the liability for the breach of obligations, the fulfilment of which is essential for the proper execution of the contract and on the observance of which the customer may regularly rely, remains unaffected. The same applies to breaches of duty by our agents.

This technical datasheet is created automatically and is valid without signature.

