



Schill+Seilacher

Technical Data Sheet

STRUKTOL® HT 257

Processing additive for the rubber industry

Composition

Compound of fatty acid and amino acid derivatives

Properties

| | | |
|-------------------------|----------------------|---------------------------------------|
| Appearance | | beige pastilles |
| Density | [kg/m ³] | 1000 |
| Dropping point | [°C] | 75 |
| Acid value | [mg KOH/g] | 120 |
| Physiological behaviour | | refer to safety data sheet |
| Storage stability | | at least 24 months if stored properly |
| Packaging | | 20 kg bags |

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.



Bank: Commerzbank AG, Hamburg, BIC: COBA DE FFXXX
 IBAN: DE07 2004 0000 0613 1254 00
 Bank: DZ Bank, Hamburg, BIC: GENO DE FF200
 IBAN: DE74 2006 0000 0000 1461 68
 Bank: Commerzbank AG, Hamburg, BIC DRES DE FF200
 IBAN: DE45 2008 0000 0275 0570 00
 Bank: Svenska Handelsbanken AB (publ), Frankfurt, BIC HAND DE FFXXX
 IBAN: DE31 5142 0600 0012 4460 01

Sitz der Gesellschaft:
 Hamburg
 Registergericht:
 Handelsregister Hamburg
 HRB 112163
 ID-Nr. DE 813088647
 Steuer-Nr. 46/757/00201
 Gesellschaft mit
 beschränkter Haftung

Hausanschrift/Address:
 Moorfleeter Straße 28
 22113 Hamburg
 Postfach: 74 07 60
 22097 Hamburg, Germany
 Geschäftsführer:
 Dr. Rüdiger Ackermann

4.19-1-01-01-(5)
 + 49 40 733 62-0
 Telefon:
 Fax:
 Verkauf: + 49 40 733 62-194
 Einkauf: + 49 40 733 62-39222
 Zentrale: + 49 40 733 62-194
 Geschäftsleitung: + 49 40 733 62-124
 E-Mail: info@struktol.de
 Internet: www.struktol.de

**Schill+Seilacher**

Recommendations for Application

STRUKTOL® HT 257 is a processing additive for the application in highly filled rubber compounds. Due to its distinctively surface-active properties this product supports especially the distribution of anorganic fillers, e.i. silica. It reduces the tendency of re-agglomeration of filler particles during the following storage so that the increase of viscosity which often can be observed is clearly reduced.

STRUKTOL® HT 257 was developed especially for the application in silica filled compounds for the tread application but it also can be used favourably in other highly filled compounds based on unpolar rubbers.

Dosage

1 – 3 phr

The suggestions for application and usage of our products as well as possible proposed formulations are meant to advise only to the best of our knowledge. This information is without obligation and does not release customers from their own testings to ensure suitability for intended processes and use. Liability is only accepted in case of intention or gross negligence. Liability for any defects caused by minor negligence are not accepted. Each producer is responsible and liable to observe legislation and patent rights of third parties.

This new leaflet replaces all previously printed documentation.

Alterations reserved. 12/2017

Schill + Seilacher "Struktol" GmbH Moorfleeter Straße 28 22113 Hamburg Germany
Phone: +49 40 73362-0 Fax: +49 40 73362-194 E-Mail: info@struktol.de