



Schill + Seilacher

Technical Data Sheet

STRUKTOL® LA 190

Antioxidant Dispersion for Latex

Composition

Aqueous dispersion of butylated reaction product of p-cresol and dicyclopentadiene

Properties

Appearance		whitish liquid
Solids content	[%]	40
pH-value		9,4
Viscosity at 20 °C	[mPa·s]	1750
Physiological behaviour		refer to safety data sheet
Storage stability		at least 6 months under normal storage conditions. Product should be stirred thoroughly before application Transport and storage at temperatures above 6 °C is imperative
Packing		900 kg containers or 200 kg drums

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.



Schill + Seilacher "Struktol" GmbH
Moorfleeter Str. 28
D-22113 Hamburg

Fon: +49 40 733 62-0
Fax: +49 40 733 62-194
E-Mail: info@struktol.de
Internet: www.struktol.de

Recommendations for Application

The antioxidant contained in STRUKTOL LA 190 exhibits high activity, low volatility and provides good colour stability.

STRUKTOL LA 190 is recommended for improved ageing performance of latex goods based on following polymers: NR, IR, SBR, CR, carboxylated SR latices and dispersion of resins.

Dosage

0.5 - 3 phr

The suggestions for application and usage of our products as well as possible proposed formulations are meant to advise only to the best of our knowledge. This information is without obligation and does not release customers from their own testings to ensure suitability for intended processes and use. Liability is only accepted in case of intention or gross negligence. Liability for any defects caused by minor negligence are not accepted. Each producer is responsible and liable to observe legislation and patent rights of third parties.

This new leaflet replaces all previously printed documentation.

Alterations reserved. 07/2003

Schill + Seilacher "Struktol" GmbH Moorfleeter Straße 28 22113 Hamburg Germany
Phone: +49 40 73362-0 Fax: +49 40 73362-194 E-Mail: info@struktol.de