

**Schill + Seilacher**

Technical Data Sheet

**STRUKTOL<sup>®</sup> LA 331**

Antioxidant Dispersion for Latex

**Composition**

Aqueous dispersion of hindered alkylated phenols, a sulphur-containing synergist (1 : 1), and anionic surfactants

**Properties**

Appearance		pale-yellow liquid
Solids Content	[%]	50
Physiological behaviour		refer to safety data sheet
Storage stability		at least 6 months under normal storage conditions. Product should be stirred thoroughly before application. Transport and storage at temperatures above 6 °C is imperative
Packing		900 kg containers or 200 kg drums

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.



**Schill + Seilacher "Struktol" GmbH**  
**Moorfleeter Str. 28**  
**D-22113 Hamburg**

Fon: +49 40 733 62-0  
 Fax: +49 40 733 62-194  
 E-Mail: [info@struktol.de](mailto:info@struktol.de)  
 Internet: [www.struktol.de](http://www.struktol.de)

## **Recommendations for Application**

STRUKTOL LA 331 contains non-staining antioxidants and is recommended for latex articles based on NR, SBR and XSBR.

## **Dosage**

0.3 – 1.5 phr

The suggestions for application and usage of our products as well as possible proposed formulations are meant to advise only to the best of our knowledge. This information is without obligation and does not release customers from their own testings to ensure suitability for intended processes and use. Liability is only accepted in case of intention or gross negligence. Liability for any defects caused by minor negligence are not accepted. Each producer is responsible and liable to observe legislation and patent rights of third parties.

This new leaflet replaces all previously printed documentation.

Alterations reserved. 02/2011

Schill + Seilacher "Struktol" GmbH Moorfleeter Straße 28 22113 Hamburg Germany  
Phone: +49 40 73362-0 Fax: +49 40 73362-194 E-Mail: info@struktol.de